




(43) International Publication Date
16 September 2004 (16.09.2004)

PCT

(10) International Publication Number
WO 2004/078652 A1

- | | |
|---|---|
| <p>(51) International Patent Classification⁷: C01G 25/00, 25/02</p> <p>(21) International Application Number: PCT/KR2003/002619</p> <p>(22) International Filing Date: 1 December 2003 (01.12.2003)</p> <p>(25) Filing Language: English</p> <p>(26) Publication Language: English</p> <p>(30) Priority Data: 10-2003-0014245 7 March 2003 (07.03.2003) KR</p> <p>(71) Applicant (for all designated States except US): KO-REAN RESEARCH INSTITUTE OF CHEMICAL TECHNOLOGY [KR/KR]; 100 Jang-dong, Yuseong-ku, Daejeon 305-343 (KR).</p> <p>(72) Inventors; and</p> <p>(75) Inventors/Applicants (for US only): KIM, Hee Young [KR/KR]; 101-203 Hanbit Apartment, Eoeun-dong,</p> | <p>Yuseong-ku, Daejeon 305-755 (KR). PARK, Yong Ki [KR/KR]; 119-302 Hanbit Apartment, Eoeun-dong, Yuseong-ku, Daejeon 305-755 (KR). YOON, Kyung Koo [KR/KR]; 126-903 Hanbit Apartment, Eoeun-dong, Yuseong-ku, Daejeon 305-755 (KR). LIM, Hyung Sup [KR/KR]; 218-401 Hanyang Apartment, Sunbu-dong 1086, Ansan 425-140, Kyungki-do (KR).</p> <p>(74) Agents: BAEK, Duk Yeul et al.; 18th Floor, Marine Center Main Building, 118 Namdaemun-ro 2-ka, Chung-gu, Seoul 100-770 (KR).</p> <p>(81) Designated States (national): CN, JP, US.</p> <p>(84) Designated States (regional): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).</p> <p>Published:
— with international search report</p> <p><i>For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.</i></p> |
|---|---|

(54) Title: METHOD FOR CONTINUOUS PREPARATION OF NANOMETER-SIZED HYDROUS ZIRCONIA SOL



(57) Abstract: The present invention relates to a method a method for continuous preparation of a well dispersed spherical hydrous zirconia particles with an average diameter (d_p) of 1~1,000 nm in the form of sol solution, which method comprises continuously supplying the aqueous solution of a zirconium salt at a concentration of 0.001~0.5 mole/l to a reactor consisting of one or more than two reaction tubes at a temperature of less than 25°C, heating the said aqueous solution in the reactor(s) in a continuous flow state up to the boiling point, and then discharging the said solution through the outlet of the said reactor(s). Contrary to the method employing a conventional batch-type reactor or semi-continuous stirred-type reactor, the method for continuous preparation of a hydrous zirconia sol according to the present invention can allow various operational parameters to be controlled in a certain range and thus contributes to remarkably improve the quality of a hydrous zirconia sol to be prepared or of the zirconia powder obtainable as a final product.